

Tremco Incorporated certifies that Tremco 2550 asphalt protection board (1/8") meets the physical properties outlined in the Tremco Incorporated published data sheets, specifications, and application instructions. This product exhibits the typical physical properties as shown herein:

**Tremco® 2550**

Asphalt Protection Board 1/8"

**TYPICAL PHYSICAL PROPERTIES**

PROPERTY	TYPICAL VALUES
Puncture Resistance at 94°C	200 psi
Indentation	Less than 0.9 mm
Density, lb / ft <sup>3</sup>	88 lb/ft <sup>3</sup>
Weight, lb / ft <sup>2</sup>	0.92
Bitumen Content, % by weight	0.45
Inert Residual, % by weight	0.55
Binders, Fiberglass (both sides)	Full width inorganic nonwoven matting
Binders, % inorganic	100%
Bitumen Softening Point °C	108 °C
Anti-Stick Material	Polyethylene film
Alkali Attack	No disintegration
Binders, Tensile Strength	
Width, lb	24 lb
Length, lb	33 lb
Water Absorption, % weight increase (after 80 hours at 60 °C)	0.26%
Water Permeability (after 1 month)	No leakage, swelling or deterioration